



DESCRIPTION		Artic-Forum- Fusion-Metallica		Brazilia-Costa Rica Indiana
Total thickness	EN 428	mm	3.25/3.30	3.00
Thickness of wearlayer	EN 429	mm	1.00/1.12 / 1.27 /1.17	1.02/0.97
Weight	EN 430	g/m ²	3130/3150/3260	2800
Width of sheet	EN 426	cm	200	200
Length of sheet	EN 426	lm	25	25
CLASSIFICATION				
Norm / Product specification	-	-	EN 651	
European classification	EN 685	class	34-42	
Fire rating	EN 13 501- 1	class	Cfl-s1	
Static electrical propensity	EN 1815	kV	< 2	
Slip resistance wet: ramp test with oil	DIN 51 130	class	R10	
PERFORMANCES				
Wear resistance	EN 660.2	mm ₃	< 2.0	
Wear group	EN 651	-	T	
Dimensional stability	EN 434	%	≤ 0.40	
Residual indentation (exigency)	EN 433	mm	≤ 0.20	
Residual indentation (measure)	-	mm	0.10	
Impact sound insulation	EN ISO 717-2	dB	16	
Thermal conductivity	EN 12 524	W/(m.K)	0.25	
Colour fastness	EN 20 105 - B02	degree	≥ 6	
Chemical products resistance	EN 423	-	OK	
Anti-bacterial and fungicidal treatment	-	-	Sanosol®	
Surface treatment	-	-	Protecsol®	
CE MARKING				
	EN 14041	-		
		-		